

## AVKOTE 8048 Silver Primer

### Description

Base of Binder:	Two component low solvent priming coat.
Recommended Use:	Especially for steel surfaces, which can not be sandblasted, perfect for renovation. The paint can be applied straight onto rusty surfaces.
Binder:	Epoxyresin
Characteristics:	Excellent adhesion even on hot dip galvanised surfaces and outstanding substrate wetting (solvent < 5%).
Delivery Specifications	
Colour:	Silver
Gloss:	Satin Glossy
Hardener:	AVKOTE 8049 Hardener

### Technical Data

Density:	1.45 g/cm <sup>3</sup>
Solids Including Hardener:	97% ± 2%
Mixing Ratio:	1:1 with AVKOTE 8049 Hardener NS by volume / weight
Potlife at 10°C	4 hours
Drying Conditions:	Dust Dry in 6 hours Touch Dry in 24 hours
Storage life in tightly closed containers at 20°C	Lacquer 12 months Hardener 6 months In closed original buckets, store dry and cool (0-20°C)

### Application Instructions

Surface Preparation	SA 2 resp. ST 3 according to Ö Norm DIN 55928
Thinner	AVKOTE 3000 Thinner
Application Method:	Brushing, roller coating, spraying, airless add possibly up to 10% AVKOTE 3000 Thinner
Cleaning of Equipment:	Immediately after use with AVKOTE 3000 Thinner or gun wash.

### Structure

Substrate	All surfaces must be clean, grease and dust free.
Recommended Structure:	Surface Steel : manual de-rusting SST3 1-2 x AVKOTE 8048 Silver Primer

This information is a standard recommendation. The application should be adapted to local standards. No liability or claim can be made from this sheet.