

Technical Data Sheet



Edition dated: 07.03.06

Replaces Edition dated: 27.05.03

Data sheet Nr. 5494/GL

AVKOTE Glass Lacquer

Product description	Air-drying two-component clear lacquer	
Binding Agent	Polyurethane / acrylic resin combination	
Areas of Application	Air-drying clear lacquer for high-quality coating of Glass. Interior use only.	
Form of Supply	Colours	Clear
	Gloss Level	Satin Gloss
Hardener	AVKOTE 279 Hardener	
Packing	Coating	1, 3 and 5 Litre disposable containers
	Hardener	1 Litre disposable containers

Technical Data


The data is valid for AVKOTE Glass Lacquer. The values can change for other colours.							
	Coating		Hardener		Mixture		
Specific Gravity (23 °C)	0.96	g/cm ³	0.99	g/cm ³	0.97	g/cm ³	
Solids content	33 ± 2 Weight-%		46 ± 2 Weight-%		37 ± 2 Weight-%		
Organic Solvent Content.	67 ± 2 Weight-%		54 ± 2 Weight-%		63 ± 2 Weight-%		
VOC Content (CH / EU)	64.5	%	645	g/l	53.4	%	534 g/l
Shelf life at 20 °C	6 Months						
Theoretical Coverage	125 g/m ² →8		m ² /kg for 40		µm dry layer thickness		

Safety Data	Coating		Hardener	
Flash point	-5 °C		0 °C	
Transport ADR/RID	Class: 3	VP: II	Class: 3	VP: III
Poison classification (EU)				
VVS disposal code (EU/CH)	08, 08 01, 08 01 11		08, 08 01, 08 01 11	










Application Recommendations




Substrate	No. of Coats	Product	Dry Film thickness	Data sheet
Glass	1 x Lacquer	AVKOTE Glass Lacquer	30-50 µm	5494/GL
For further application proposals please ask our technical department.				

Preparation

	Substrate	Every substrate must be thoroughly cleaned, grease and oil-free, and dry before paint application commences.
	Glass	The glass must be well cleaned and degreased using only AVKOTE Glass Cleaner and 100% lint free cotton cloth . Other cloths e.g. paper or man-made cloths must NOT be used for surface preparation. AVKOTE Glass Cleaner must be used to clean the glass as some Glass Cleaners may leave a residue on the glass which could affect the adhesion. Since there are different types of glass, it is recommended always to do a small test prior to the complete application. To maintain levels of quality, any coating should always be applied to the air side.

Processing

	Preventative measures	We recommend the wearing of protective clothing even if not stipulated by law. The national and regional health and safety regulations for work hygiene and equipment are to be observed. Pay attention to our safety data sheet Nos. 148500 and 279H00.				
	Stir	Before use ensure contents are stirred together well with hardener if applicable.				
	Mixing Ratio	4 : 1 by volume with AVKOTE 279 Hardener				
	Pot life at 20 °C	8 Hours				
	Thinners	Supplied ready to spray				
	brush	Not recommended				
	Roll	Not recommended				
		Viscosity DIN-4	Thinners	Nozzle	Pressure	Spray coats
	Gravity Feed Spray-gun	16-20" DIN-4	10%	1.4 - 1.8 mm	3 - 4 bar	2
	Suction-spray-gun	18 - 22 secs	25 - 30 %	1.4 - 1.8 mm	3 - 4 bar	2
	Airless-(Airmix)-Spray	22 - 25" secs	25 %	11/40	3 – 4 bar Atomising air 1.5 - 2	1 - 2

	HVLP paint gun	18 - 22 secs	25 - 30 %	1.4 - 1.8 mm	3 - 4 bar	2
	Evaporation time	Prior to drying at temperatures over 40°C allow an evaporation time of 15 minutes.				
	Drying time	For 40 µm dry coating at 65 % of relative humidity				
	At 20 °C	Tack-Dry	after:	10	Minutes	
		Touch – Dry	after:	60	Minutes	
		Dried (Can be sanded)	after:	2	Hours	
		Suitable for re-coating	after:	2	Hours	
		Completely Dry	after:	10	days	

Important references

Specific restrictions	Relative humidity max. 80 %		
Minimum application- and drying temperature	15	°C	Do not apply at temperatures below the dew point
Coating removal	With paint stripper		
Recoating	Lightly sand and spray with AVKOTE Glass Lacquer		
Equipment cleaning	Clean immediately after use with Gun Wash Thinners or U Cleaner.		

This data sheet is for your reference and information only. The above data are correct to the best of our knowledge. We offer no guarantees for use and exclude any liability. This applies in particular to consequential damage. We are not liable for any advice given by our employees. Our employees give non-binding information only. Site supervision, compliance with handling regulations and adherence to recognized engineering rules are the responsibility of the manufacturer, even if our employee was on site during handling. Modifications due to technical developments may be made. The latest version of this information is applicable. In special cases, please request separate technical specifications.